

Specificaties German Pellets

		ENplus A1	DINplus	GP
Diameter	mm	6 ± 1,0 of 8 ± 1,0	6 ± 1,0 of 8 ± 1,0	6 ± 1,0 of 8 ± 1,0
Lengte	mm	3,15 ≤ L ≤ 40	3,15 ≤ L ≤ 40	3,15 ≤ L ≤ 40
Calorische waarde	MJ/kg	16,5 ≤ Q ≤ 19,0	16,5 ≤ Q ≤ 19,0	18,0 ≤ Q ≤ 19,0
Watergehalte	%	≤ 10,0	≤ 10,0	7,0 – 9,0
Fijnstofaandeel (< 3,15mm)	%	≤ 1,0	≤ 1,0	≤ 1,0
Schuring	%	≤ 2,5	≤ 2,3	< 1,5
Asgehalte	%	≤ 0,7	≤ 0,7	≤ 0,7
Asverwekingstemperatuur	°C	≥ 1200	k.A.	ca.1400
Pershulpmiddel %	%	≤ 2,0	≤ 2,0	≤ 2,0
Bulkdichtheid	kg/m ³	≥ 600	≥ 600	≥ 600
Zwavelgehalte	%	≤ 0,03	≤ 0,03	≤ 0,03
Stikstofgehalte	%	≤ 0,3	≤ 0,3	≤ 0,3
Chloorgehalte	%	≤ 0,02	≤ 0,02	≤ 0,02

**german
pellets**



ID.-Nr. 01001

